


Particle Size Distribution Test Report
IS EN933 – 1: 2012
Washing and sieving

Client Name	Fairways Sands	Scheme / Site	Quality Control
F.A.O.	John Breslin	Material	Sand for Polishing Filters
	Hollywood	Specification	Not Disclosed
	Co Wicklow		
<hr/>			
Sample No.	A17009/1	Date Sampled	Not Disclosed
Client Ref:	Washed Wicklow Granite	Date Received	18/06/2015
Location	Not Disclosed	Test Commenced	24/06/2015
Lorry Registration	Not Disclosed	Condition of sample as received:	Satisfactory
Docket No.	Not Disclosed	Supplier:	Fairways Sands

Sieve Aperture	% By Mass Passing Sieve
16mm	100
10mm	100
8mm	100
6.3mm	100
5mm	100
4mm	100
2.8mm	98
2mm	90
1mm	64
0.500mm	32
0.250mm	11
0.125mm	4
0.063mm	1.2



Remarks	Sampled By Client Certificate of sampling enclosed Mass of test portion - 1324g Uniformity Coefficient =4 (Determined in accordance with BS6100 : 1992 : clause 2.2.1) D10 = 0.23 mm
----------------	--

Authorized By : *Michael Quinn*
☒ Michael Quinn Head of Laboratory ☐ Elsa Fitzpatrick Production Manager
☐ Gerald Roche Technical / Quality Manager