

Traditional Undercoat

Technical Data Sheet - F213


PRODUCT DESCRIPTION & USE

Fleetwood Traditional Undercoat is a premium quality, alkyd based undercoat formulated for interior and exterior use on wood and metal surfaces. It provides the perfect surface for over-coating with Fleetwood Gloss or Satinwood bases

KEY BENEFITS

- An alkyd resin based undercoat for interior and exterior . use.
- Excellent opacity and obliteration qualities.
- Produces the perfect surface for over-coating with Fleetwood gloss or satinwood paints.

AVAILABLE IN SIZES



COLOUR RANGE

Fleetwood Traditional High Gloss White and various pre-packaged colour

VOC CONTENT

Contains max VOC; 296g/l Conforms to EU 2010 Directive (Cat A/d) 300g/l

COMPOSITION (NOMINAL)

Pigment:	Lightfast Pigments.
Binder:	Long oil alkyd resin
Solvent:	De-aromatized white spirit

SOLIDS - SPECIFIC GRAVITY

Volume Solids	63% (+/- 2%)
Weight Solids	82% (+/-2%)
Specific Gravity	1.70g/l (+/- 0.05)

SURFACE PREPARATION

All surfaces must be clean, dry and free from all defective or poorly adhering material. Thoroughly rub down previously painted surfaces, using 'wet "flatting' methods where possible, wipe off with a damp, lint free cloth. Treat knots with a suitable knotting solution. New or bare surfaces should be primed with an appropriate primer. Note: Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain lead (Pb). Use in accordance with good painting practices

APPLICATION



This product may be spray applied but for H&S reasons related to all solvent-based paints, spray application is not recommended. As with other solvent-based paints, do not apply in temperatures below 5ºC (as recommended by British Standard BS 6150).

SPREADING RATE



As a guide a coverage rate of up to 16m² per litre can be achieved under normal conditions

TRANSPORTATION & STORAGE

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

SPRAY RECOMMENDATIONS

Conventional Spray: Satisfactory through most equipment. Airless Spray: A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm^2 (2000 lb/sq in) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 2 - 4 hours 16 - 24 hours

Hard Drv -48 hours This is dependent upon temperature and

humidity. Darker colors may take longer. 26°C to 50% RH @ 4 Thou wet

CLEANING UP

Recoat:



Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with White Spirit or Turpentine Substitute. Dispose of cans and waste paint in accordance with local authority guidelines

TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. Flammable- keep away from sources of ignition. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. Contains no added lead.

PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. If paint is peeling or badly weathered, clean to sound substrate and treat as new.

FOLLOW US ON

Online:	www.fleetwood.ie
Email:	info@fleetwood.ie
Phone:	049 8547209

-f 🔰 🗿 🔯